



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>6</sup> :</b> <b>C07D 213/89</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 98/41505</b> <b>(43) International Publication Date:</b> 24 September 1998 (24.09.98)
<b>(21) International Application Number:</b> PCT/US98/04139 <b>(22) International Filing Date:</b> 4 March 1998 (04.03.98)  <b>(30) Priority Data:</b> 60/040,793 14 March 1997 (14.03.97) US 09/032,959 2 March 1998 (02.03.98) US  <b>(71) Applicant:</b> OLIN CORPORATION [US/US]; 350 Knotter Drive, P.O. Box 586, Cheshire, CT 06410-0586 (US).  <b>(72) Inventors:</b> POLSON, George, A.; 131 Campville Hill Road, Harwinton, CT 06791 (US). DUMAS, Richard, H.; 2 Brockett Place, East Haven, CT 06512 (US). HANI, Rahim; 148 Fairway Drive, Cheshire, CT 06410 (US).  <b>(74) Agents:</b> GARABEDIAN, Todd, E. et al.; Wiggin & Dana, One Century Tower, New Haven, CT 06508-1832 (US).		<b>(81) Designated States:</b> AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, GW, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZW, Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).  <b>Published</b> <i>With international search report.</i>
<b>(54) Title:</b> METHOD FOR PRODUCING PARTICLES OF PYRITHIONE SALTS  <b>(57) Abstract</b>  The present invention relates to a method for producing submicron-sized particles of pyrithione salts, comprising reacting pyrithione or a water-soluble salt of pyrithione and a water-soluble polyvalent metal salt in a pressurized turbulent flow reactor that generates pulverizing forces, the reaction producing submicron sized particles of pyrithione salt. The present invention also relates to particles made by the above method, and products, such as shampoos, soaps, and skin care medicaments made using these particles.		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU*	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

METHOD FOR PRODUCING PARTICLES  
OF PYRITHIONE SALTS

5           The present invention relates generally to a  
method for preparing particles of pyrithione salts, and  
more specifically to a method of preparing submicron-  
sized particles of pyrithione salts under pressurized,  
turbulent conditions. The present invention also  
10 relates to particles made by the method, as well as  
products made with the particles produced by the  
method.

Polyvalent metal salts of pyrithione (also known  
as 1-hydroxy-2-pyridinethione; 2-pyridinethiol-1-oxide;  
15 2-pyridinethione; 2-mercaptopyridine-N-oxide;  
pyridinethione; and pyridinethione-N-oxide) are known  
to be effective biocidal agents, and are widely used as  
fungicides and bactericides in paints and personal care  
products such as anti-dandruff shampoos. The  
20 polyvalent metal salts of pyrithione are only sparingly  
soluble in water and include magnesium pyrithione,  
barium pyrithione, strontium pyrithione, copper  
pyrithione, zinc pyrithione, cadmium pyrithione, and  
zirconium pyrithione. The most widely used divalent

-2-

pyrithione salts are zinc pyrithione and copper pyrithione.

Zinc and copper pyrithione are useful as antimicrobial agents active against gram-positive and negative bacteria, fungi, and yeasts. Zinc pyrithione is used as an antidandruff component in shampoos, while technical suspensions of zinc pyrithione and/or copper pyrithione are used as preservatives and antifouling agents in paints and polymers. Synthesis of polyvalent pyrithione salts are described in U.S. Patent No. 2,809,971 to Bernstein et al. Other patents disclosing similar compounds and processes for making them include U.S. Patent Nos. 2,786,847; 3,589,999; 3,590,035; 3,773,770.

Known methods for producing insoluble polyvalent salts of pyrithione result in large solid particles having an average size greater than 2 micrometers ( $\mu\text{m}$ ). However, smaller particles of pyrithione salts (i.e., less than 1 micrometer or submicron) are often desired because they more easily form suspensions and provide a larger surface area for enhanced biocidal activity. In addition, smaller particles, particularly in the low submicron range (e.g., below about 0.2  $\mu\text{m}$ ), are transparent to light, and thus provide the opportunity

- 3 -

to manufacture "clear" products, such as clear shampoos and soaps, that are popular in the marketplace today.

Smaller particles of pyrithione salts are usually generated by a separate mechanical manipulation step  
5 (e.g., grinding or crushing) on larger particles or crystals that are made by conventional processes. For example, European Patent No. 70046 describes preparation of zinc pyrithione using organic solvents. This process results in production of large crystals of  
10 zinc pyrithione that are easily isolated by filtration. A separate, optional grinding step is used to grind the large crystals and produce zinc pyrithione particles of smaller size.

As another example, U.S. Patent No. 4,670,430  
15 describes a process of making zinc pyrithione particles with a median size of about 0.2  $\mu\text{m}$  by grinding larger zinc pyrithione particles.

There is currently no single step method for producing particles of pyrithione salts in the  
20 submicron size range. The separate step of grinding larger particles to produce smaller particles, as described in the prior art, generally results in substantial loss of useful product, and is costly in terms of equipment, time, and energy required.

- 4 -

Accordingly, what is needed in the art is a method to prepare pyrithione salt particles in the submicron size range without a separate mechanical crushing or grinding step. The present invention is believed to be  
5 an answer to that need.

In one aspect, the present invention relates to a method for producing submicron-sized particles of pyrithione salts, comprising reacting pyrithione or a water-soluble salt of pyrithione and a water-soluble  
10 polyvalent metal salt in a pressurized turbulent flow reactor that generates pulverizing forces, the reaction producing submicron sized particles of pyrithione salt.

In another aspect, the present invention relates to a method for producing submicron-sized particles of  
15 zinc pyrithione comprising reacting a pyrithione or a water-soluble salt of pyrithione and a water-soluble zinc salt selected from the group consisting of zinc sulfate, zinc chloride, zinc acetate, and combinations thereof, in a turbulent flow reactor generating  
20 pulverizing forces, the turbulent flow reactor maintained at a pressure of from about 18,000 psi to about 23,000 psi and a temperature of from about 0°C to about 23°C, the reaction producing submicron-sized particles of zinc pyrithione.

-5-

In yet another aspect, the present invention relates to particles produced by the above methods, and products made using particles made by the method of the invention.

5        These and other aspects will become apparent upon reading the following detailed description of the invention.

It now has been surprisingly found, in accordance with the present invention, that a solution is provided to the problem of efficiently producing pyrithione salt particles of submicron size in a single operation. The present inventors have solved this problem by reacting pyrithione or a water-soluble salt of pyrithione, and a water-soluble polyvalent metal salt in a pressurized, turbulent flow reactor that generates pulverizing forces. The pulverizing forces produced by the pressurized, turbulent flow reactor efficiently generate pyrithione salt particles of submicron size without resorting to a separate mechanical grinding or crushing step. The submicron-sized pyrithione salt particles made by the method of the invention have a narrow and uniform size distribution, and have excellent surface deposition properties due to the large surface area provided by the population of

10  
15  
20

-6-

submicron particles. This large surface area results in improved biocidal efficacy in shampoos, soaps and paints. In addition, the submicron-sized particles made according to the method of the invention more  
5 easily form suspensions when combined with other compounds, and the suspensions thus formed have greater physical stability against settling of the particles.

As used herein, the term "water-soluble salts of pyrrithione" or "water-soluble pyrrithione salts" include  
10 those salts of pyrrithione in which the hydrogen atom of the thiol group is substituted with a monovalent cation. The term "water-soluble polyvalent metal salt" refers to those salts in which the cation has a charge of +2 or greater. The terms "elevated pressure" and/or  
15 "pressurized" are defined herein as any pressure greater than about 1 atm. The terms "turbulent" and "turbulence" refer to departure in a fluid from a smooth flow where the velocity of the fluid at a given point varies erratically in magnitude and direction.  
20 The term "flow reactor" refers to a device which manipulates a fluid stream containing reactants, products, reaction medium, or a combination thereof. The term "pulverizing forces" is defined herein as those forces which affect particle size reduction under



- 7 -

turbulent flow conditions, such as shear forces, impact forces, cavitation forces, sonication forces, or combinations of these. The term "submicron" is defined herein as any size less than 1 micrometer ( $\mu\text{m}$ ).

5 Preferred ranges of submicron particles are from about 0.01  $\mu\text{m}$  to about 0.99  $\mu\text{m}$ . The terms "particles of pyrrithione salts" and "pyrrithione salt particles" as used herein refer to those salts of pyrrithione that form precipitates and are essentially insoluble or  
10 sparingly soluble in the surrounding medium.

In accordance with the process of the present invention, pyrrithione or a water-soluble salt of pyrrithione is reacted with a water-soluble salt of a selected polyvalent metal in a pressurized turbulent  
15 flow reactor that generates pulverizing forces. The pulverizing forces generated under the pressure and turbulence of the flow reactor efficiently reduce the pyrrithione salt particles produced by the reaction to submicron size as they are formed. Pyrrithione in its  
20 acid form, or a water-soluble salt of pyrrithione may be used in the reaction. Useful water soluble salts of pyrrithione preferably include an ammonium ion or an alkali metal ion. Accordingly, exemplary water soluble salts of pyrrithione include sodium pyrrithione,

potassium pyrithione, lithium pyrithione, ammonium pyrithione, and combinations thereof. The most preferred water-soluble salt of pyrithione in the present invention is the sodium salt (i.e., sodium pyrithione). The amount of pyrithione or water-soluble salt of pyrithione can vary over a wide range, and establishing a useful amount is understood to be within the capabilities of the ordinary skilled practitioner based on the stoichiometry of the reaction and the required amount of submicron particles of pyrithione salt that must be generated. A preferred amount of pyrithione or water-soluble pyrithione salt is from about 3% to about 52% by weight of the total weight of the reaction mixture.

Exemplary water-soluble polyvalent metal salts useful in accordance with the method of the invention include zinc salts, tin salts, cadmium salts, copper salts, zirconium salts, magnesium salts, aluminum salts, and the like. Combinations of these salts may also be employed. Useful counterions for these metals include nitrates, acetates, sulfates, halides or combinations thereof. Preferred water-soluble polyvalent metal salts include zinc chloride ( $\text{ZnCl}_2$ ), copper chloride ( $\text{CuCl}_2$ ), zinc acetate ( $\text{ZnO}_2\text{CCH}_3$ ) and

zinc sulfate ( $\text{ZnSO}_4$ ). The amount of water-soluble polyvalent metal salt may vary depending on the amount of pyrithione or water-soluble salt of pyrithione used in the reaction. The molar ratio of pyrithione or  
5 water-soluble salt of pyrithione to the water-soluble polyvalent metal salt is generally in the range from about 1:2 to about 1:8. Preferably, a slight stoichiometric excess (e.g., 5% of water-soluble polyvalent metal salt by weight over pyrithione or  
10 water-soluble salt of pyrithione) is desirable to ensure a complete reaction.

Useful media for the reaction include aqueous media such as water, or water in combination with one or more organic solvent(s). Useful organic solvents  
15 include alcohols, such as methanol, ethanol, amines such as diethanolamine, ether, esters, and the like.

Additional materials, such as dispersants may be added to the reactants during the precipitation reaction to prevent agglomeration of the pyrithione  
20 salt particles. Alternatively, the dispersant may be added at the completion of the reaction to prevent particle agglomeration. Preferably, the dispersant is a salt of polymerized alkyl naphthalene sulfonic acid, such as "DARVAN 1" (sodium naphthalene sulfonic acid

-10-

formaldehyde, a product of R.T. Vanderbilt Co. Inc.),  
"DEMOL N" (sodium salt of naphthalene sulfonic acid, a  
product of Kao Chemicals), "DAXAD 11" (sodium salt of  
polymerized alkyl naphthalene sulfonic acids, a product  
5 of W.R. Grace & Co.), "TAMOL N" (sodium salt of  
condensed naphthalene sulfonic acid, a product of Rohm  
and Haas Co.), "HAROL KG" (potassium salts of  
polymerized alkyl naphthalene sulfonic acids, a product  
of Graden Chemical Co.), "HAROL RG-71" (sodium salts of  
-10- polymerized alkyl naphthalene sulfonic acids, a product  
of Graden Chemical Co.), "LOMAR LS" (sodium salt of  
condensed mononaphthalene sulfonic acid, a product of  
Henkel Corp.) and the like. Additional useful  
dispersants are disclosed in McCutcheons Handbook of  
15 Functional Materials (North American Volume I, 1992, pp  
117-137). Combinations of two, three, four, or more  
dispersants as described herein may also be used  
according to the invention.

The dispersants employed in the method of the  
20 present invention may suitably be combined with a  
surfactant. Useful surfactants may be selected from  
the classes of surfactants known as nonionics,  
anionics, cationics, and amphoterics (the latter being  
also commonly referred to as "zwitterionics"). The

- 11 -

surfactants are suitably employed singly, or in combinations of two, three, or even four or more surfactants selected from the above-mentioned four classes.

5           Useful nonionic surfactants include linear alcohol alkoxylates, such as the linear alcohol ethoxylates, ethoxylated/propoxylated block copolymers, ethoxylated/propoxylated fatty alcohols, and polyoxyethylene cetyl ethers, and the like. Useful  
10 linear alcohol alkoxylates are commercially available, for example, under the registered trademark POLY-TERGENT SL-42, a product of Olin Corporation. If desired, the alcohol alkoxylate is suitably end-capped with a lower alkyl group, and such a product is  
15 commercially available as POLY-TERGENT SLF-18, a propylene oxide-capped linear alcohol alkoxylate that is also a product of Olin Corporation, and these end-capped linear alcohol alkoxylates are notably low foaming during use. Also advantageous for use in  
20 accordance with the present invention are surfactants within the group commercially available as POLY-TERGENT SLF-18B series surfactants, which are surfactants characterized by enhanced biodegradability (also products of Olin Corporation), being alkene oxide-

-12-

capped linear alcohol alkoxyates, containing ethylene oxide moieties in the backbone, and suitably also containing at least one propylene oxide moiety in the backbone, as disclosed, for example, in U.S. Patents  
5 4,925,587 and 4,898,621.

Other useful nonionic surfactants include one commercially available as NEODOL 91-6, a registered trademark surfactant product of Shell Chemical. This surfactant is a detergent range mixture of C<sub>9</sub>-C<sub>11</sub> linear  
10 primary alcohol ethoxylates having an average of six moles of ethylene oxide per mole of alcohol. Other useful nonionic surfactants include those containing a linear C<sub>9</sub>-C<sub>11</sub> carbon chain and five or six ethylene oxide or propylene oxide groups per molecule.

15 Useful anionic surfactants include alkyl diphenylether disulfonates, alkyl phenyl ethoxylated phosphate esters, carboxylated linear alcohol alkoxyates, linear alkyl benzene sulfonic acid, diisobutyl sulfosuccinate, and alkyl sulfonates.  
20 Useful anionics also include the alkylated diphenyl oxide sulfonates, and their methods of preparation are well-known, as illustrated by the disclosures of U.S. Patents 3,264,242; 3,634,272; and 3,945,437.

Commercial methods of preparation of the alkylated

-13-

diphenyl oxide sulfonates generally do not produce species which are monoalkylated, monosulfonated, dialkylated or disulfonated. The commercially available species typically are predominately (greater  
5 than 90 percent) disulfonated and are a mixture of mono- and di- alkylated with the percentage of dialkylation being about 15 to about 25 percent, and the percentage of monoalkylation being about 75 to 85 percent. Most typically, the commercially available  
10 species are about 80 percent monoalkylated and 20 percent dialkylated.

Two illustrative commercially available solutions containing alkylated diphenyl oxide sulfonate surfactants are DOWFAX 8390 and DOWFAX 8390A  
15 surfactants, trademarked products of The Dow Chemical Company. In each, the alkyl group is predominantly a hexadecyl  $C_{16}$  group. These products are suitably employed in a solution fully or partially neutralized with ammonium hydroxide if desired.

20 An advantageous anionic surfactant is also provided by reacting the above-described alkylated diphenyl oxide sulfonates with a piperazine compound to produce a molar ratio of sulfonate compound to piperazine compound of between about 10:1 and about

-14-

1:10, preferably between about 2:1 and about 1:2.

Although any piperazine compound can be used for such reaction, preferred compounds include those selected from the group consisting of 1,2-aminoethyl piperazine,  
5 1,4-piperazinediethane sulfonic acid, anhydrous piperazine, hydrated piperazine, and combinations thereof.

Other useful anionics are polycarboxylated alcohol alkoxylates, preferably those selected from acids or  
10 organic or inorganic salts of the following:  
polycarboxylated linear alcohol alkoxylates,  
polycarboxylated branched alcohol alkoxylates,  
polycarboxylated cyclic alcohol alkoxylates, and combinations thereof. These polycarboxylated alcohol  
15 alkoxylates typically contain at least two succinic acid radicals per molecule. Preferred polycarboxylated alcohol alkoxylates are those having a backbone containing both poly(propylene oxide) and poly(ethylene oxide) blocks, and such preferred polycarboxylated  
20 alcohol alkoxylates are readily commercially available, for example, as POLY-TERGENT CS-1, a trademarked surfactant of Olin Corporation. If desired, at least a portion of the acid groups on the polycarboxylated alcohol alkoxylate are neutralized with a base to



-15-

provide the corresponding salt. Suitable bases include alkali metal hydroxides, alkaline earth metal hydroxides, and metal-free hydroxides, including potassium hydroxide, ammonium hydroxide, calcium hydroxide, magnesium hydroxide, ammonia, mono-, di- and tri-ethanol amines, and combinations thereof. Sodium hydroxide is preferred, and although potassium hydroxide can be employed, it is not preferred. The organic or inorganic base is preferably employed in at least an equimolar amount relative to the number of moles of polycarboxylated alcohol alkoxyated used. The polycarboxylated alcohol may also contain a polycarboxylic acid, for example, polyacrylic acid, along with the starting alcohol alkoxyate and esters of the alkoxyate of the polycarboxylic acid.

Although individually the cationic and the amphoteric surfactants are acceptable for use in the process of the present invention, they may also be used in combination with at least one surfactant from one of the other classes. Illustrative cationics include alkyl triammonium halide, non-linear alkyl dimethyl halide and alkyl dimethyl benzyl ammonium halide-containing surfactants. Illustrative amphoteric

-16-

surfactants include polyglycol ether derivatives, ethoxylate oxazoline derivatives, lauramidopropyl betaine, and lecithin.

Suitable blends can be employed in the process of the present invention based on various combinations of the above-described surfactants. Such a blend can be any combination of two or more surfactants, between or within the above-described four broad classes of surfactants. Combinations can include blends of:

10 anionic with anionic, anionic with nonionic, anionic with cationic, anionic with amphoteric, cationic with cationic, cationic with amphoteric, nonionic with nonionic, nonionic with amphoteric, and amphoteric with amphoteric. Likewise, ternary and quaternary blends of

15 surfactants by selecting three or four surfactants, respectively, from within or among the above-described classes.

Suitably, any single or combination of two, three or four surfactants from the following illustrative

20 list are suitably employed: (a) nonionics, including alkoxylated linear alcohols (such as POLY-TERGENT SLF-18 surfactant, a product of Olin Corporation), linear alcohol ethoxylates (such as NEODOL 91-8 surfactant, a product of the Shell Corporation), ethoxylated linear

-17-

alkyl benzene (such as TRITON X-100 surfactant, a product of Union Carbide Corporation), and EO/PO block copolymers (such as POLY-TERGENT E-17A surfactant, a product of Olin Corporation); (b) anionics, including

5 alkyl diphenyl ether disulfonates (such as POLY-TERGENT 2A1 surfactant, a product of Olin Corporation), alkyl phenyl ethoxylated phosphate esters (such as Wayfos M-60 surfactant, a product of Olin Corporation),

carboxylated linear alcohol alkoxylates (such as POLY-10 TERGENT CS-1 surfactant, a product of Olin Corporation), linear alkyl benzene sulfonic acid (such as BIOSOFT S-130 surfactant, a product of Stepan Company), alpha-olefin sulfonates (such as BIO TERG AS-40 surfactant, a product of Stepan Company),

15 dialkylsulfosuccinates (such as AROWET SC-75 surfactant, a product of Arol Chemical Products), and alkyl sulfates (such as STEPANOL SLS surfactant, a product of Stepan Company); (c) cationics including

alkyl triammonium halides (such as CTAB surfactant, a 20 product of VWR Scientific Inc.), polyoxyethylene cocoamine (such as MAZEEN surfactant, a product of PPG Industries), primary alkyl amines (such as ARMEEN surfactant, a product of Akzo Chemical Co.), dicoco dimethyl ammonium halide (such as JET QUAT surfactant,

-18-

a product of Jetco Chemical Inc.), di-isodecyl dimethyl ammonium halides (such as AMMONYX K9 surfactant, a product of Stepan Company), and diethyl aminoethyl stearate (such as CERASYNT 303 surfactant, a product of  
5 ISP Van Dyke); and, (d) amphoterics, including polyglycol ether derivatives (such as ALBEGAL A surfactant, a product of Ciba-Geigy), ethoxylated oxazolin derivatives (such as ALKATERG T-IV surfactant, a product of Angus Chemicals), lauramide propyl betain  
10 (such as LEXAINE C surfactant, a product of Inolex Chemicals), lecithin (such as CANASPERSE surfactant, a product of Can Amoral), disodium cocoamphodiacetate (such as MONATERICS surfactant, a product of Mona Industries), complex fatty amine salt (such as MAFO 13  
15 surfactant, a product of PPG Industries), and cocoamine oxide (such as MACKAMINE CO surfactant, a product of the McIntyre Group Ltd.).

The dispersant or dispersant/surfactant combination is preferably employed in a total amount of  
20 between about 0.05 and 10%, more preferably between about 0.1 and 5%, most preferably between about 0.5 and about 1.5% by weight, based on the total weight of the reaction mixture.

-19-

In order to efficiently produce submicron-sized particles of pyrrithione salt, the reactants are reacted in a flow reactor under conditions of high pressure and turbulence. The combination of high pressure and  
5 turbulence generates pulverizing forces within the flow reactor and affects size reduction of the pyrrithione salt particles simultaneously as they are formed in the reaction. In a preferred embodiment, sodium pyrrithione is reacted with zinc chloride, zinc sulfate, zinc  
10 acetate, or a combination thereof in a flow reactor that generates pulverizing forces (e.g., Model M-140K Laboratory Microfluidizer Processor available from Microfluidics International Corp., Newton MA). The reaction products are submicron-sized particles of zinc  
15 pyrrithione, along with aqueous sodium chloride, aqueous sodium sulfate, or aqueous sodium acetate as by-products.

Pressure may be generated in the flow reactor by any method known in the art, such as by pump, piston,  
20 and the like. In one embodiment, the reactants are pumped under high pressure into a mixing chamber via air-powered pumps. The high pressure capabilities of the pumps result in generation of pressures on the reactants as high as about 50,000 psi. Preferably,

-20-

pressures useful in the reaction are in the range of 10,000 to 50,000 psi, more preferably in the range of 18,000 to 23,000, and most preferably in the range of 18,000 to 20,000 psi.

5           Turbulence may be generated in the flow reactor by perturbing the pressurized laminar flow of the reaction mixture as it passes through the flow reactor.

Turbulence may be generated by any means known in the art. However, the pressurized laminar flow of the

10 reaction mixture must be perturbed to an extent sufficient to generate pulverizing forces that affect size reduction of the pyrrithione salt particles. In one embodiment, baffles may be placed in the flow reactor to perturb the laminar flow of reactants as

15 they move through the flow reactor under high pressure. In another embodiment, the pressurized reaction mixture (which may include pyrrithione salt particles and aqueous by-products) is passed through a fixed geometry interaction chamber where it is divided into a

20 plurality of streams, for example two streams. The streams are then brought together such that the high pressure and turbulent forces of stream convergence result in overall particle size reduction by generation of pulverizing forces. The size reducing forces

generated by stream convergence include, for example, shear forces, impact forces, cavitation forces, and the like, or combinations of these, and result in effective size reduction of the particles.

5           The interaction chamber apparatus may be used in a "single-pass" mode to subject newly-generated pyrithione salt particles to size reduction forces only once. Alternatively, the pyrithione salt particles may be repeatedly subjected to the forces generated in the  
10 interaction chamber by repeatedly dividing and reconverging the reaction mixture in a "multiple-pass" mode. The interaction chamber may be fitted with cooling or heating coils to maintain a desired temperature.

15           In general, higher pressures produce smaller particles in accordance with the method of the invention. As an example, pressures of about 10,000 psi produce particles in the range of about 0.7 to 0.95  $\mu\text{m}$ . Pressures of about 18,000 psi generally produce  
20 particles in the range of about 0.3 to 0.4  $\mu\text{m}$ . Accordingly, one skilled in the art can easily modify the pressures to attain populations of desired particle sizes.

-22-

The temperature of the reaction and flow reactor may be maintained at any temperature which permits precipitation of pyrithione salt. Generally, lower temperatures promote the formation of smaller particles; therefore, lower temperatures are preferred. Accordingly, the reaction temperature is preferably between the freezing point of the aqueous medium and ambient temperature (about 23°C), more preferably between about 0 and about 15°C, and most preferably between about 0°C and about 7°C. A particularly useful temperature range is from about 5 to about 7°C.

The particles of insoluble pyrithione salt made by the method of the invention have a narrow submicron size range, preferably in the range of about 0.03  $\mu\text{m}$  to about 0.95  $\mu\text{m}$ , more preferably in the range of about 0.04  $\mu\text{m}$  to about 0.88  $\mu\text{m}$ , and most preferably in the range of about 0.30  $\mu\text{m}$  to about 0.45  $\mu\text{m}$ . The pyrithione salt particles may be isolated from the by-products by filtration or other isolation methods known in the art. Alternatively, the mixture of particles and by-products may be added to commercial products directly without further purification. The by-products (e.g., aqueous sodium chloride, aqueous sodium sulfate, or aqueous sodium acetate) are useful in shampoo or



-23-

soap formulations as thickeners. Addition of the combination of pyrithione salt particles and by-products made in accordance with the present invention is efficient from a manufacturing standpoint due to the large cost savings in eliminating separation, isolation and purification steps.

The particles produced according to the method of the invention are useful as additives in a variety of items such as personal care products (soaps, shampoos, and the like), paints, coatings, fertilizers, and foodstuffs. For example, zinc pyrithione particles made according to the method of the invention are a useful antidandruff additive to antidandruff shampoos.

15

## EXAMPLES

The following examples are intended to illustrate, but in no way limit the scope of the present invention. All parts and percentages are by weight and all temperatures are in degrees Celsius unless explicitly stated otherwise. In the following Examples "q.s." means quantity sufficient, generally 0.1 to 2% by weight.

20

EXAMPLE 1: Production of Submicron Particles of Zinc Pyrithione

-24-

A solution of 24 g of 20%  $\text{ZnSO}_4$ , 0.5 g "DARVAN" (sodium salt of polymerized alkyl naphthalene sulfonic acids) and 25.5 g of water is introduced into and recirculated through a model M-140K Laboratory

5 Microfluidizer Processor (Microfluidics International Corp., Newton MA) which included a fixed geometry interaction chamber. The entire apparatus is cooled to approximately  $7^\circ\text{C}$ , and pressure is maintained in the Microfluidizer at about 18,000 psi. A solution of

10 sodium pyrithione (45 mL of a 16.3% solution) is added to the inlet of the reservoir of the Microfluidizer over an 8 minute period, and circulation of the reactants continued for 5-10 minutes. As the reaction mixture circulated through the Microfluidizer

15 apparatus, the fixed geometry interaction chamber divides the reaction mixture into two streams. The streams are then brought together under pressure to generate turbulence and pulverizing forces that result in size reduction of the zinc pyrithione particles.

20 The particles of zinc pyrithione thus formed are measured by a laser light scattering particle size analyzer (Horiba LA910). Table I shows the size distribution and frequency of the particles. The median particle size is approximately  $0.313\ \mu\text{m}$ . The

-25-

particle size distribution is very narrowly dispersed (nearly mono dispersed) and exhibits a size range from about 0.30 to about 0.45  $\mu\text{m}$ .

Table I

Size ( $\mu\text{m}$ )	Frequency (%)	Cumulative (%)
0.445	0.25	100.0
0.389	22.41	99.75
3.39	64.35	77.34
0.296	13.00	13.00

5

EXAMPLE 2: Production of Submicron Particles of Copper Pyrrithione

In a manner similar to Example 1, 100 mL of a 3% aqueous solution of sodium pyrrithione is introduced into and recirculated through a Microfluidizer apparatus maintained at about 20,000 psi and at approximately 5°C. 50 mL of a 2.42%  $\text{CuCl}_2$  solution is added to this circulating solution which is maintained at 5°C. The size and distribution of particles of copper pyrrithione generated from one pass through the Microfluidizer is measured using a Horiba LA910 laser. Analysis revealed that the particle sizes ranged from 0.04 to 0.88  $\mu\text{m}$ , with a median size of about 0.09  $\mu\text{m}$ .

20 EXAMPLE 3: (Proposed Example) Antidandruff Shampoo

Formulation I

-26-

An antidandruff shampoo composition is made using the zinc pyrithione particles made as described in Examples 1 and 2 in combination with the following ingredients:

## 5   Component A:

Water	41.0%
Magnesium aluminum silicate	1.0%
Hydroxypropyl methylcellulose	0.8%

## Component B:

10    Zinc Pyrithione (needles/rods, 25% aqueous dispersion)	4.0%
---	------

## Component C:

Cocamide DEA	1.0%
--------------	------

## Component D:

15    Triethanolamine lauryl sulfate, 40%	40.0%
Triethanolamine, 99%	3.2%
FD&C Blue No. 1 (0.2%)	1.5%
FD&C Yellow No. 5 (0.1%)	0.5%
Fragrance	q.s.

20

The antidandruff shampoo composition was made as follows:

Component A is prepared by heating water to 70°C and dissolving the other two components with stirring (about 1500 rpm). The temperature of the mixture is lowered to 50°C, and Component B is added, and stirring continued for 5 minutes. Stirring speed is reduced to ~300 RPM. Component C is melted in a separate

-27-

container, and added to the A/B mixture. The heat is removed and component D is added while the mixture cools.

5 EXAMPLE 4: (Proposed Example) Antidandruff Shampoo

Formulation II

Another antidandruff shampoo composition is made using the zinc pyrithione particles made as described in Examples 1 and 2 in combination with the following

10 ingredients:

Component A:

Deionized water	76.0%
Ammonium lauryl sulfate °	15.0%
Cocamide DEA	2.0%

15 Component B:

Di(hydrogenated) tallow phthalic acid amide	5.0%
Zinc Pyrithione (needles/rods, 25% aqueous dispersion)	4.0%

20 Component C:

Preservative	q.s.
--------------	------

Component D:

Citric Acid, 50% aq. Solution, OR	
Sodium hydroxide, 50% aqueous solution	q.s.

25 Component E:

Ammonium chloride	q.s.
-------------------	------

-28-

The antidandruff shampoo composition is made as follows:

In separate containers, components A and B are each mixed well. Component A is heated to 60°C and  
5 component B is added. The mixture is stirred for 30 minutes. The mixture is then cooled to 50°C, and component C is added. The pH of the resulting mixture is adjusted to 5.0-6.2 with component D, and the viscosity is adjusted with component E.

10

EXAMPLE 5: (Proposed Example) Antidandruff Shampoo with Conditioner I

An antidandruff shampoo and conditioner composition is made using the zinc pyrithione particles  
15 made as described in Examples 1 and 2 in combination with the following ingredients:

Component A:

	Deionized Water	77.0%
	Ammonium lauryl sulfate	20.0%
20	Cocamide DEA	2.0%

Component B:

	Di(hydrogenated) tallow phthalic acid amide	4.0%
	Zinc Pyrithione (needles/rods, 25% aqueous dispersion)	4.0%
25	Dimethicone, 12,000 cps	0.5%

Component C:

-29-

Preservative q.s.

Component D:

Citric acid, 50% aqueous solution, OR  
Sodium hydroxide, 50% aqueous solution q.s.

5 Component E:

Ammonium chloride q.s.

The antidandruff shampoo and conditioner  
composition is made as follows:

10 In separate containers, components A and B are  
each mixed well. Component A is heated to 60°C and  
component B is added. The mixture is stirred for 30  
minutes. The mixture is then cooled to 50°C, and  
component C is added. The pH of the resulting mixture  
15 is adjusted to 5.0-6.2 with component D, and the  
viscosity is adjusted with component E.

EXAMPLE 6: (Proposed Example) Antidandruff Shampoo with  
Conditioner II

20 Another antidandruff shampoo and conditioner  
composition is made using the zinc pyrithione particles  
made as described in Examples 1 and 2 in combination  
with the following ingredients:

Component A:

25 Deionized water 21.75%  
Guar hydroxypropyl trimonium chloride 0.30%  
Magnesium Aluminum Silicate 0.70%

-30-

	Zinc Pyrithione (needles/rods, 25% aqueous dispersion)	4.0%
	Component B:	
	Sodium laureth sulfate	30.0%
5	Ammonium xylene sulfonate, 40% aq.	02.0%
	Component C:	
	Tricetylammonium chloride	0.50%
	Cetyl alcohol NF	0.40%
	Stearyl alcohol	0.40%
10	Glycol distearate	2.00%
	Component D:	
	Cocamide MEA	1.70%
	Ammonium lauryl sulfate	36.00%
	Component E:	
15	Preservative	0.05%
	Fragrance and dye	q.s.
	Component F	
	Citric acid, 25% aqueous solution	q.s.

20 The antidandruff shampoo and conditioner  
composition is made as follows:

Component A is prepared by heating water to 50°C  
and dispersing the guar hydroxypropyl trimonium  
chloride and the magnesium aluminum silicate with rapid  
25 agitation. The zinc pyrithione dispersion is added to  
this combination with stirring. The pH of component A  
is adjusted to 4.5-5.0 with component F. Both  
components of B are slowly added to component A, mixing  
well. The pH of the mixture is adjusted to 5.7-6.3



-31-

with component F. In a separate container, component C is heated to 70-75°C. The A/B mixture is heated to 60°C and blended with component C, mixing well. Both components of D are added to the hot mixture, and  
5 stirred well. The pH of the mixture is adjusted to 5.7-6.3 with component F. The mixture is cooled to 40-45°C, and component E is added with stirring. If desired, the viscosity of the product can be increased by adding 0.05-1% sodium chloride.

10

EXAMPLE 7: (Proposed Example) "Extra Body" Antidandruff Shampoo

An "extra body" antidandruff shampoo and conditioner composition is made using the zinc  
15 pyrithione particles made as described in Examples 1 and 2 in combination with the following ingredients:

Component A:

	Deionized Water	62.6%
20	Zinc Pyrithione (needles/rods, 25% aqueous dispersion)	4.0%

Component B:

	Methyl Paraben	0.30%
	Propyl Paraben	0.10%
	Propylene Glycol	0.50%
25	Sodium Chloride	0.50%

Component C:

	Triethanolamine lauryl sulfate	20.0%
--	--------------------------------	-------

-32-

	Cocamide MEA	4.0%
	Ethylene glycol distearate	7.0%
	Component D:	
	Cocodimonium hydrolyzed animal protein	1.00%
5	Component E:	
	FD&C Blue No. 1	q.s.
	Component F:	
	Citric Acid, 50% aqueous solution	q.s.

10       The antidandruff shampoo and conditioner  
composition is made as follows:

Component A is heated to 60°C. The ingredients of  
component B are added with good stirring until  
dissolved. The ingredients of component C are added to  
15 the mixture sequentially, and heated with mixing at  
60°C. The mixture is cooled with stirring to 40°C, and  
components D and E are added with stirring. The pH of  
the final composition is adjusted to 4.7 with component  
F.

20

Although the invention has been shown and  
described with respect to illustrative embodiments  
thereof, it should be appreciated that the foregoing  
and various other changes, omissions and additions in  
25 the form and detail thereof may be made without

-33-

departing from the spirit and scope of the invention as delineated in the claims.

- 34 -

WHAT IS CLAIMED IS:

1. A method for producing submicron-sized particles of pyrrhithione salts, characterized by reacting  
5 pyrrhithione or a water-soluble salt of pyrrhithione and a water-soluble polyvalent metal salt in a pressurized turbulent flow reactor that generates pulverizing forces, said reaction producing submicron sized particles of pyrrhithione salt.  
10
2. The method of claim 1, characterized in that said water-soluble salt of pyrrhithione is selected from the group consisting of sodium pyrrhithione, potassium pyrrhithione, lithium pyrrhithione, ammonium pyrrhithione,  
15 and combinations thereof.
3. The method of claim 1, characterized in that said water-soluble polyvalent metal salt is a divalent salt selected from the group consisting of zinc salts, tin  
20 salts, cadmium salts, bismuth salts, copper salts, zirconium salts, magnesium salts, aluminum salts, nitrate salts, acetate salts, sulfate salts, halide salts, and combinations thereof.

-35-

4. The method of claim 3, characterized in that said divalent salt is selected from the group consisting of zinc sulfate, zinc chloride, zinc acetate, copper chloride, and combinations thereof.

5

5. The method of claim 1, characterized in that said reacting step further comprises adding a dispersant selected from the group consisting of sodium salts of polymerized alkyl naphthalene sulfonic acids, and

10 combinations thereof.

6. The method of claim 5, characterized in that said dispersant is present in a blend with a surfactant.

15 7. The method of claim 1, characterized in that the ratio of said pyrrhione or water-soluble salt of pyrrhione to said water-soluble polyvalent metal salt is in the range from about 1:2 to about 1:8.

20 8. The method of claim 1, further characterized by the step of isolating said submicron particles of pyrrhione salt.

-36-

9. The method of claim 1, characterized in that the pressure maintained in said pressurized turbulent flow reactor is greater than 1000 psi.

5 10. The method of claim 1, characterized in that said reacting step takes place at a temperature of from about 0°C and about 23°C.

10 11. The method of claim 1, characterized in that said pulverizing forces are selected from the group consisting of shear forces, impact forces, cavitation forces, sonication forces, and combinations thereof.

15 12. The method of claim 1, characterized in that said submicron-sized particles of pyrrithione salt have sizes in the range of about 0.03  $\mu\text{m}$  to about 0.95  $\mu\text{m}$ .

20 13. The method of claim 12, characterized in that said submicron-sized particles of pyrrithione salt have sizes in the range of about 0.04  $\mu\text{m}$  to about 0.88  $\mu\text{m}$ .

14. The method of claim 13, characterized in that said submicron-sized particles of pyrrithione salt have sizes in the range of about 0.30  $\mu\text{m}$  to about 0.45  $\mu\text{m}$ .

-37-

15. A shampoo or skin-care composition characterized by a base fluid and submicron particles of pyrithione salts made by the method of claim 1.

5 16. The composition of claim 15, characterized in that said base fluid is selected from the group consisting of surfactants, dispersants and combinations thereof.

17. A method for producing submicron-sized particles  
10 of zinc pyrithione, characterized by reacting a pyrithione or a water-soluble salt of pyrithione and a water-soluble zinc salt selected from the group consisting of zinc sulfate, zinc chloride, zinc acetate, and combinations thereof, in a turbulent flow  
15 reactor generating pulverizing forces, said turbulent flow reactor maintained at a pressure of from about 18,000 psi to about 23,000 psi and a temperature of from about 0°C to about 23°C, said reaction producing submicron-sized particles of zinc pyrithione.

-38-

18. The method of claim 17, characterized in that said water-soluble salt of pyrithione is selected from the group consisting of sodium pyrithione, potassium pyrithione, lithium pyrithione, ammonium pyrithione,  
5 and combinations thereof.

19. The method of claim 17, characterized in that said reacting step further comprises adding a dispersant selected from the group consisting of sodium salts of  
10... polymerized alkyl naphthalene sulfonic acids, and combinations thereof.

20. The method of claim 19, characterized in that said dispersant is present in a blend with a surfactant.

15

21. The method of claim 17, characterized in that the ratio of said pyrithione or a water-soluble salt of pyrithione to a water-soluble polyvalent metal salt is in the range from about 1:2 to about 1:8.

20

22. The method of claim 17, further characterized by the step of isolating said submicron particles of zinc pyrithione.



-39-

23. The method of claim 17, characterized in that said pulverizing forces are selected from the group consisting of shear forces, impact forces, cavitation forces, sonication forces, and combinations thereof.

5

24. The method of claim 17, characterized in that said submicron particles of zinc pyrithione have sizes in the range of about 0.03  $\mu\text{m}$  to about 0.95  $\mu\text{m}$ .

10 25. The method of claim 24, characterized in that said submicron particles of zinc pyrithione have sizes in the range of about 0.04  $\mu\text{m}$  to about 0.88  $\mu\text{m}$ .

15 26. The method of claim 25, characterized in that said submicron particles of zinc pyrithione have sizes in the range of about 0.30  $\mu\text{m}$  to about 0.45  $\mu\text{m}$ .

20 27. A shampoo or skin-care composition, characterized by a base fluid and submicron-sized particles of zinc pyrithione made by the method of claim 17.

28. The composition of claim 27, characterized in that said base fluid is selected from the group consisting of surfactants, dispersants, and combinations thereof.

## INTERNATIONAL SEARCH REPORT

International application No.  
PCT/US98/04139

## A. CLASSIFICATION OF SUBJECT MATTER

IPC(6) :C07D 213/89

US CL :546/293

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 546/293

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

CAS ONLINE

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 4,323,683 A (BOLICH, Jr. et al.) 06 April 1982, entire document	1-28
Y	US 5,104,645 A (CARDIN et al.) 14 April 1992, entire document	1-28
Y	US 5,230,833 A (ROMBERGER et al.) 27 July 1993, entire document	1-28
Y, P	US 5,723,110 A (YAMAMOTO et al.) 03 March 1998, entire document	1-28
Y	US 4,940,578 A (YOSHIHARA et al.) 10 July 1990, entire document	1-28



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents:	*T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
*A* document defining the general state of the art which is not considered to be of particular relevance	*X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
*E* earlier document published on or after the international filing date	*Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
*L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	* & * document member of the same patent family
*Q* document referring to an oral disclosure, use, exhibition or other means	
*P* document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search

26 MAY 1998

Date of mailing of the international search report

06 JUL 1998

Name and mailing address of the ISA/US  
Commissioner of Patents and Trademarks  
Box PCT  
Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

MATTHEW V. GRUMBLING

Telephone No. (703) 308-1235